



## PATENT ABSTRACTS OF JAPAN

(11) Publication number: **60025542 A**(43) Date of publication of application: **08.02.85**

(51) Int. Cl. **B01J 23/89**  
**B01D 53/36**  
**B01J 23/34**  
**B01J 23/78**  
**B01J 32/00**  
**F23C 11/00**

(21) Application number: **58133807**(22) Date of filing: **21.07.83**(71) Applicant: **MATSUSHITA ELECTRIC IND CO LTD**(72) Inventor: **FUKUDA AKIO**  
**MAKI MASAO**(54) **NOX REDUCING METHOD**

## (57) Abstract:

**PURPOSE:** To achieve the catalytic decomposition of  $\text{NO}_x$  by bringing a catalyst formed by supporting a platinum group element by perovskite type composite oxide into contact with  $\text{NO}_x$ -containing gas at 800W1,000°C under an inert atmosphere.

**CONSTITUTION:** 0.1wt% or more of platinum and 0.1wt%

or more of cobalt are supported by perovskite type composite oxid represented by  $\text{ABO}_3$  (wherein an A-site is La or Sr and a B-site is Fe, Co or Mn) to obtain a catalyst. This catalyst is brought into contact with  $\text{NO}_x$ -containing gas at 800W1,000°C under an inert atmosphere or a reductive atmosphere. By this method, the reduction of  $\text{NO}_x$  is achieved.

**COPYRIGHT:** (C)1985,JPO&Japio